

PRODUCT INFORMATION

1. PRODUCT NAME

Classic Max™

LD-C-50-v2

ICYNENE Classic Max™ is a trademark for light density, open celled, flexible, 100% water-blown polyurethane foam insulation manufactured by Icynene Inc. ICYNENE Classic Max™ spray formula is a nominal 0.5 lbs/ft³ density, free rise material.

2. MANUFACTURER

ICYNENE Classic Max™ (LD-C-50-v2) is made on-site from liquid components manufactured by Icynene Inc. Installation and on-site manufacturing is supplied by independent Icynene Licensed Dealers.

3. PRODUCT DESCRIPTION

ICYNENE Classic Max™ is a light density formulation of spray foam insulation. Icynene is the pioneer of high yield, 100% waterblown polyurethane foam technology for air sealing and insulating buildings.

ICYNENE Classic Max™ insulates and airseals in one step for maximum energy conservation while minimizing the environmental impact during manufacturing and construction. Significantly reducing air leakage means ICYNENE Classic Max™ contributes to a healthier, quieter and more comfortable indoor environment, while reducing energy consumption and related greenhouse gas emissions by as much as 50%.

ICYNENE Classic Max™ is an effective vapor permeable air barrier material that can move with the building to maintain the air barrier characteristic against energy-robbing air leakage for the life of the building. Convective air movement inside wall cavities is virtually eliminated, providing more uniform temperatures throughout the building.

The result is superior quality construction, with higher comfort levels and lower heating

and/or cooling costs. Energy savings will vary depending on building design, location, etc.

ICYNENE Classic Max™ is applied by spraying liquid components onto an open wall, crawl space, ceiling surface or cathedral ceiling. There it expands approximately 100:1 in seconds to provide a flexible foam blanket of millions of tiny air cells, filling building cavities, cracks and crevices in the process. It adheres to most construction materials, sealing out air infiltration. Excess material is easily trimmed off, leaving a surface ready for drywall or other code-compliant finish.

4. TECHNICAL DATA

(Based on Core Samples)

Thermal Performance

Thermal resistance (ASTM C518)

- R/in = R3.7 hr. ft² °F/BTU

Average insulation contribution in a full fill stud wall:

- 2" x 4" = R13

- 2" x 6" = R20

ICYNENE Classic Max™ provides more effective performance than the equivalent R-value of air permeable insulation materials. ICYNENE Classic Max™ is not subject to loss of R-value due to aging, windy conditions, settling, convection or air infiltration; nor will it be prone to traditional moisture intrusion via air leakage.

Air Permeance/Air Barrier /Air Seal

ICYNENE Classic Max™ fills any shaped cavity, and adheres to most construction materials, creating assemblies with very low air permeance. Additional interior or exterior air infiltration protection is subject to applicable codes.

Air permeability of core foam:

ASTM E283

- 0.009 L/s.m² @ 75 Pa for 3.5"

Air permeability of a 2" x 6" wood framed wall assembly:

ASTM E2178

- 0.01 L/ s.m² @ 75 Pa for 5.5"

All buildings insulated and air-sealed with ICYNENE Classic Max™ must be designed to include adequate mechanical ventilation/ outdoor air supply. See ASHRAE Standard 62 – Ventilation for Acceptable Indoor Air Quality.

Water Vapor Permeance

ICYNENE Classic Max™ is water vapor permeable and allows moisture to diffuse through the insulation and dissipate from the building envelope.

Water vapor transmission properties:

(ASTM E96 Desiccant Method)

- 11 perms @ 5.5"

In those situations that warrant a vapor retarder, a supplemental layer of polyethylene may be used. Alternately, low vapor permeance paint either directly on the foam or as a primer for the interior drywall may be used.

Water Absorption Properties

Water can be forced into the foam under pressure because it is open celled. Water will drain by gravity, given favorable drying potential, and upon drying all chemical and physical properties are fully restored.

Acoustical Properties

Performance in a 2" x 4" wood stud wall:

STC Sound Transmission Class - 37

Hz. Freq. 125 250 500 1000 2000 4000

ASTM E90 19 30 31 42 38 46

NRC Noise Reduction Coeff. - .70

Hz. Freq. 125 250 500 1000 2000 4000

ASTM C423 .11 .43 .89 .72 .71 .67

Burn Characteristics

ICYNENE Classic Max™ is a combustible product and is therefore, consumed by flame, but will not sustain flame upon removal of the flame source. It leaves a charred foam residue. It will not melt or drip. ICYNENE Classic Max™ is subject to all applicable National/State and County building codes regarding fire prevention. Requirements for Thermal Barrier and Ignition Barrier coverings must be met as per the applicable building code having jurisdiction.



U.S. Fire Testing

Surface Burning Characteristics (ASTM E84) @ 5" thickness

Flame Spread ≤25
Smoke Development ≤450

*flame spread rating not intended to reflect hazards under actual fire conditions.

Unvented Attic

ICYNENE Classic Max™ can be applied to the underside of the roof deck and be left bare if its thickness is a minimum of 5½ inches at roof decking and 1½ inches at roof framing to a maximum of 20". Refer to evaluation report for details.

Electrical Wiring

ICYNENE Classic Max™ has been evaluated with energized 14/3 and 12/2 residential wiring (max. 122 ° F). It is chemically compatible with typical electrical wiring coverings. Note: For any insulation of older knob and tube wiring, please reference local electrical code.

Corrosion

ICYNENE Classic Max™ did not cause corrosion when evaluated in contact with steel at 120°F and 85% relative humidity conditions.

Plastic Piping

ICYNENE Classic Max™ is compatible in direct contact with CPVC piping systems, as per Paschal Engineering Study for the Spray Polyurethane Foam Alliance (SPFA).

Bacterial or Fungal Growth and Food Value

Independent testing conducted by Texas Tech University has confirmed that ICYNENE Classic Max™ is not a source of food for mold; and as an air barrier material, it resists the airborne introduction of moisture, nutrients, and mold spores into the building envelope.

Environmental / Health / Safety

ICYNENE Classic Max™ is 100% waterblown and therefore contains no ozone depleting blowing agents. It is also PBDE-free. It has been thoroughly evaluated for in-situ emissions by industry and government experts. VOC emissions are below 1/100th of the safe concentration level (TLV) within hours following the application of ICYNENE Classic Max™.

Proper handling and use is required to avoid exposure to reactive chemicals in their unreacted state. For more information, contact the Spray Polyurethane Foam Alliance or the

American Chemistry Council. Newly insulated areas have been shown to be safe for occupancy 24 hours after installation is complete.

ICYNENE Classic Max™ is CHPS E.Q. 2.2/Section 01350 Compliant and listed as such in the Collaborative for High Performance Schools (CHPS) Low Emitting Materials (LEM) Table.

The reaction used to create ICYNENE Classic Max™ generates carbon dioxide to expand the foam. Carbon dioxide has a very low Global Warming Potential (GWP of 1). Not intended for exterior use. Not to be installed within 3" of heat emitting devices or where the temperature is in excess of 200°F, as per ASTM C411 or in accordance with applicable codes.

5. INSTALLATION

ICYNENE Classic Max™ is installed by a network of Licensed Dealers, trained in the installation of ICYNENE Classic Max™. Installation is generally independent of environmental conditions. It can be installed in hot, humid or freezing conditions. Surface preparation is generally not necessary. Within seconds, the foaming process is complete.

For information on Health and Safety, refer to the Spray Polyurethane Foam Alliance Health and Safety guidance documents at www.spraypolyurethane.com.

6. AVAILABILITY

Contact Icynene at 1-800-758-7325 or visit our website at www.icynene.com.

7. WARRANTY

WHEN INSTALLED PROPERLY IN ACCORDANCE WITH INSTRUCTIONS, THE COMPANY WARRANTS THAT THE PROPERTIES OF THE PRODUCT MEET PRODUCT SPECIFICATIONS AS OUTLINED IN THIS PRODUCT SPECIFICATION SHEET. SAVE AND EXCEPT ANY EXCLUSIONS REFERENCED IN THE WARRANTY.

8. TECHNICAL

Icynene Licensed Dealers and Icynene Inc. provide support on both technical and regulatory issues. Architectural specifications in CSI 3-Part format and design details are available at our website at www.icynene.com.

9. REGULATORY

ICYNENE Classic Max™ (LD-C-50-v2) has been tested as per the requirements of the International Code Council – Evaluation Service's AC377 Acceptance Criteria (June 2011). A thorough engineering evaluation has been conducted for unvented attic fire performance requirements. The following evaluation reports apply to this product:

- ICC ESR-1826 (LD-C-50-v2)
- Based on the 3rd party test evidence submitted, this product was found to comply with:
- IRC: 2006 – 2009
 - IBC: 2006 – 2009
 - IECC: 2006 – 2009

10. RELATED REFERENCES

All physical properties were determined through testing by accredited third-party agencies. Icynene Inc. reserves the right to change specifications in its effort of continuous improvement. Please confirm that technical data literature is current.

11. PACKAGING AND STORAGE

Packaging Package	55 US gallon steel drums
Component 'A'	550 lb. per drum Base Seal® MDI
Component 'B'	500 lb. per drum ICYNENE LD-C-50-v2 B-side Resin

Storage

Component A, Base Seal® MDI and Component B, ICYNENE LD-C-50-v2 Resin ideally should be stored between 60°F and 90°F.

Component A, Base Seal®, should be protected from freezing.

Component B, ICYNENE LD-C-50v2™ Resin, can be frozen but must be protected from overheating 120°F and prolonged storage above 100°F.

Component B, ICYNENE LD-C-50v2™ Resin, may separate during storage and should be mixed thoroughly prior to use.

12. INSTALLATION SPECIFICATIONS

Must be installed by Icynene Licensed Dealers. Refer to the Icynene Installer's Manual for expanded information.



ICYNENE[®]
THE EVOLUTION OF INSULATION™

Telephone: 905.363.4040
Toll Free: 800.758.7325
www.icynene.com
inquiry@icynene.com

SL-213-02 Updated March 2013